


SPECTRUM DATA

OPTIMA AB65

DATE : Feb.24.1999

Wavelength(nm)	200	210	220	230	240	250	260	270	280	290	300	310	320	330	340
Transmissivity(%)	0.047	0.044	0.046	0.044	0.041	0.041	0.041	0.041	0.044	0.044	0.041	0.041	0.353	8.405	32.040
Wavelength(nm)	350	360	370	380	390	400	410	420	430	440	450	460	470	480	490
Transmissivity(%)	56.830	71.760	78.210	76.050	82.020	82.730	78.060	71.290	65.790	62.410	62.080	63.170	64.720	65.880	66.580
Wavelength(nm)	500	510	520	530	540	550	560	570	580	590	600	610	620	630	640
Transmissivity(%)	66.860	66.640	66.080	65.310	65.540	66.690	67.850	67.530	66.010	64.230	64.240	64.070	63.730	63.180	63.030
Wavelength(nm)	650	660	670	680	690	700	710	720	730	740	750	760	770	780	790
Transmissivity(%)	64.250	67.080	71.340	76.590	81.100	83.640	84.820	85.270	84.990	85.140	84.770	83.950	83.190	82.660	82.410
Wavelength(nm)	800	808	810	820	830	840	850	860	870	880	890	900			
Transmissivity(%)	81.530	81.160	81.020	80.370	79.990	79.130	79.240	78.450	78.250	77.930	77.080	77.88			



Color Glass Filter (OPTIMA INC. JAPAN)

- 1) Model : OPTIMA AB65
- 2) Melt No.: 961050
- 3) Size : 50mm x 50mm x 2mm t
- 4) Test No.: 991008

Inspector : Technomart Inc. Eng. Div.

SEO, IL-SOO