


SPECTRUM DATA(NIR)

OPTIMA

JB9

DATE : Sep.02. 1999

Wavelength(nm)	220	240	260	280	300	320	340	360	380	400	420	440	460	480	500
Transmissivity(%)	0.917	1.072	1.171	1.158	1.198	1.156	1.156	1.191	1.153	1.169	1.358	3.795	15.478	36.152	55.510
Wavelength(nm)	520	540	560	580	600	620	640	660	680	700	720	740	760	780	800
Transmissivity(%)	68.168	74.572	76.535	75.366	72.425	68.682	66.505	65.569	67.689	69.082	72.869	77.138	81.218	84.708	87.119
Wavelength(nm)	820	840	860	880	900	920	940	960	980	1000	1020	1040	1060	1080	1100
Transmissivity(%)	88.506	89.047	89.481	90.295	90.396	90.284	90.345	90.294	90.436	90.643	90.723	90.828	90.896	91.037	91.156
Wavelength(nm)	1130	1160	1190	1220	1250	1280	1310	1340	1370	1400	1430	1460	1490	1520	1550
Transmissivity(%)	91.336	91.370	91.453	91.565	91.670	91.732	91.705	91.699	91.611	91.568	91.716	91.789	91.835	91.827	91.925
Wavelength(nm)	1580	1610	1640	1670	1700	1730	1760	1790	1820	1850	1880	1910	1940	1970	2000
Transmissivity(%)	91.937	91.909	91.766	91.835	91.763	91.756	91.734	91.038	91.587	91.614	91.528	91.539	91.484	91.415	91.066



Color Glass Filter (OPTIMA INC. JAPAN)

- 1) Model : OPTIMA JB9
- 2) Melt No. 011013
- 3) Size : 50mm x 50mm x2mm t
- 4) Test No : 991007

Inspector : Technomart Inc. Eng. Div.

SEO, IL-SOO