


# SPECTRUM DATA

OPTIMA JB510

DATE : June, 24. 1998

Wavelength(nm)	200	210	220	230	240	250	260	270	280	290	300	310	320	330	340
Transmissivity(%)	0.026	0.023	0.024	0.021	0.023	0.020	0.021	0.023	0.023	0.023	0.023	0.026	0.026	0.026	0.028
Wavelength(nm)	350	360	370	380	390	400	410	420	430	440	450	460	470	480	490
Transmissivity(%)	0.028	0.028	0.024	0.023	0.023	0.023	0.024	0.023	0.021	0.021	0.023	0.023	0.020	0.032	1.987
Wavelength(nm)	500	510	520	530	540	550	560	570	580	590	600	610	620	630	640
Transmissivity(%)	42.470	78.300	87.100	89.670	90.640	91.090	91.360	91.450	91.530	91.490	91.490	91.450	91.390	91.340	91.280
Wavelength(nm)	650	660	670	680	690	700	710	720	730	740	750	760	770	780	790
Transmissivity(%)	91.200	91.110	91.050	91.010	90.960	90.880	90.810	90.790	90.610	90.470	90.340	90.120	90.050	89.890	89.780
Wavelength(nm)	800	810	820	830	840	850	860	870	880	890	900				
Transmissivity(%)	89.630	89.540	89.430	89.330	89.300	89.230	89.170	89.060	89.190	88.760	88.940				



## Color Glass Filter (OPTIMA INC. JAPAN)

- 1) Model : OPTIMA JB510 (SCHOTT GG515 Equivalent)
- 2) Melt No.: 970883
- 3) Size : 50mm x 50mm x 2mm t
- 4) Test No.: 9806-011

Inspector : Technomart Inc. Eng. Div.

SEO, IL-SOO